

SANTOPRENE® 8221-75M300

SANTOPRENE®

A soft, colorable, UV resistant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material is designed for automotive interior applications requiring low fogging and good appearance. This grade of Santoprene™ TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- Neutral, easy coloring formulation.
- Recommended for applications requiring excellent ozone resistance.
- Used in sealing applications.
- Recommended for applications requiring excellent flex fatigue resistance.
- Designed for improved UV resistance.

Product information

Resin Identification	TPV	ISO 1043
Part Marking Code	>TPV<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	1.6 ^[1] %	ISO 294-4, 2577
Moulding shrinkage, normal	0.9 ^[1] %	ISO 294-4, 2577

[1]: 2.0 mm thickness, min. 24 hours after molding, per test method TPE-X0080

Typical mechanical properties

Tensile stress at 100% elongation, perpendicular	3.1 MPa	ISO 37
Tensile stress at break, perpendicular	6.8 MPa	ISO 527-1/-2 or ISO 37
Elongation at break, perpendicular	490 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	75	ISO 48-4 / ISO 868

Flammability

FMVSS Class	B	ISO 3795 (FMVSS 302)
Burning rate, Thickness 2 mm	17.3 mm/min	ISO 3795 (FMVSS 302)

Physical/Other properties

Density	920 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	≥3 h
Processing Moisture Content	≤0.08 %
Melt Temperature Optimum	200 °C
Min. melt temperature	190 °C
Max. melt temperature	215 °C
Mold Temperature Optimum	35 °C
Min. mould temperature	20 °C
Max. mould temperature	50 °C

SANTOPRENE® 8221-75M300

SANTOPRENE®

Characteristics

Processing	Injection Moulding, Multi Injection Moulding
Delivery form	Pellets
Special characteristics	U.V. stabilised or stable to weather, High Flow

Additional information

Injection molding	<p>Holding pressure should be about 50 to 75% of the actual injection pressure. A high screw RPM (100 to 200) is recommended. Back pressure is not always needed, however, a back pressure of 0.3 to 0.7 MPa may be used to ensure a homogeneous melt and maintain a consistent shot size. A higher back pressure is normally employed when using masterbatches.</p>
-------------------	--

Processing Notes

Processing Notes

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene® TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC.

Santoprene® TPV has a relatively high melt viscosity at low shear rates. Viscosity decreases as the shear rate increases. Increasing temperature has little effect on TPV melt viscosity. Smaller gates and higher shear rates keep melt viscosity low and improve melt flow. Please also refer to the injection molding guide.

Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
Ford	WSS-M2D510-A7	
General Motors	GMW15816P-TPV-EPDM+PP-Class-I-Type-6	
Mercedes-Benz	DBL5562	
Stellantis	55248_02 EMP80	MS-AR-100 CMV2
VW Group	VW 50123	
VW Group	VW 50180	