

# GUR® 4056-3

GUR®

GUR 4056-3 : UHMW-PE powder grade: small hydrophilic particle

## Product information

Resin Identification	(PE-UHMW)	ISO 1043
Part Marking Code	>(PE-UHMW)<	ISO 11469
Average molecular weight	7.3E6 g/mol	Margolies' equation
Average particle size, d50	60 µm	laser scattering

## Rheological properties

Viscosity number	3200 cm <sup>3</sup> /g	ISO 307, 1628
Intrinsic viscosity	2700	ISO 307, 1628

## Typical mechanical properties

Tensile modulus	540 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	18 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	15 %	ISO 527-1/-2
Tensile stress at 50% strain	18 MPa	ISO 527-1/-2
Tensile stress at break, 50mm/min	36 MPa	ISO 527-1/-2
Nominal strain at break	380 %	ISO 527-1/-2
Elongational stress F, 150/10	0.5 MPa	ISO 21304-2
Charpy double notched impact strength, 23°C	180 kJ/m <sup>2</sup>	ISO 21304-2
Poisson's ratio	0.47 <sup>[C]</sup>	
Shore D hardness, 15s	60	ISO 48-4 / ISO 868

[C]: Calculated

## Tribological properties

Wear by sandslurry method (based on GUR 4120=100)	85
------------------------------------------------------	----

## Thermal properties

Temperature of deflection under load, 1.8 MPa	38 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	80 °C	ISO 306

## Electrical properties

Volume resistivity	1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	1E12 Ohm	IEC 62631-3-2

## Physical/Other properties

Density	930 kg/m <sup>3</sup>	ISO 1183
Bulk density	440 kg/m <sup>3</sup>	ISO 60

## Characteristics

Delivery form	Powder, Micropowder
Special characteristics	High impact or impact modified, Hydrolysis resistant, Low wear / Low friction, Chemical resistant, Hydrophilic