

GUR[®] 4113

Melt processable UHMW-PE powder grade
Melt processable UHMW-PE powder grade

Product information

Average molecular weight	3.7E6 g/mol	Margolies' equation
Average particle size, D50	120 µm	laser scattering

Rheological properties

Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	21.6 kg	
Viscosity number	1900 cm ³ /g	ISO 307, 1157, 1628
Intrinsic viscosity	1700	ISO 307, 1157, 1628

Typical mechanical properties

Tensile Modulus	800 MPa	ISO 527-1/-2
Yield stress, 50mm/min	22 MPa	ISO 527-1/-2
Yield strain, 50mm/min	12 %	ISO 527-1/-2
Stress at 50% strain	19 MPa	ISO 527-1/-2
Stress at break, 50mm/min	37 MPa	ISO 527-1/-2
Nominal strain at break	430 %	ISO 527-1/-2
Elongational stress, 150/10	0.12 MPa	ISO 21304-2
Charpy double notched impact strength, 23°C	190 kJ/m ²	ISO 21304-2
Shore D hardness, 15s	62	ISO 48-4 / ISO 868

Tribological properties

Relative Wear (based on GUR 4120=100), sandslurry method	130	Internal
---	-----	----------

Thermal properties

Vicat softening temperature, 50°C/h, 50N	80 °C	ISO 306
--	-------	---------

Electrical properties

Volume resistivity	>1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E12 Ohm	IEC 62631-3-2

Other properties

Density	930 kg/m ³	ISO 1183
Bulk density	460 kg/m ³	ISO 60

GUR[®] 4113

Characteristics

Food contact

FDA 21 CFR
