

# GUR<sup>®</sup> 4150-3 L

## GUR<sup>®</sup>

Fine particle UHMW-PE powder grade for filtration

### Product information

Resin Identification	(PE-UHMW)	ISO 1043
Part Marking Code	>(PE-UHMW)<	ISO 11469
Average molecular weight	8.1E6 g/mol	Margolies' equation
Average particle size, d50	60 µm	laser scattering

### Rheological properties

Viscosity number	3500 cm <sup>3</sup> /g	ISO 307, 1628
Intrinsic viscosity	2900	ISO 307, 1628

### Typical mechanical properties

Tensile modulus	540 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	18 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	15 %	ISO 527-1/-2
Tensile stress at 50% strain	18 MPa	ISO 527-1/-2
Tensile stress at break, 50mm/min	36 MPa	ISO 527-1/-2
Nominal strain at break	380 %	ISO 527-1/-2
Elongational stress F, 150/10	0.51 MPa	ISO 21304-2
Charpy double notched impact strength, 23°C	180 kJ/m <sup>2</sup>	ISO 21304-2
Poisson's ratio	0.47 <sup>[C]</sup>	
Shore D hardness, 15s	60	ISO 48-4 / ISO 868

[C]: Calculated

### Tribological properties

Wear by sandslurry method (based on GUR 4120=100)	85
--	----

### Thermal properties

Temperature of deflection under load, 1.8 MPa	38 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	80 °C	ISO 306

### Electrical properties

Volume resistivity	1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	1E12 Ohm	IEC 62631-3-2

### Physical/Other properties

Density	930 kg/m <sup>3</sup>	ISO 1183
Bulk density	450 kg/m <sup>3</sup>	ISO 60

### Characteristics

Processing	Porous Sintering
Delivery form	Powder, Micropowder
Special characteristics	High impact or impact modified, Hydrolysis resistant, Low wear / Low friction, Chemical resistant