

GUR[®] X 160 (PRELIMINARY)

Hydrophilic, very fine particle size, low bulk density HMW-PE powder grade
Hydrophilic, very fine particle size, low bulk density UHMW-PE powder grade, additive in thermoplastics and rubbers
/ additive in paints and lacquers

Product information

Average molecular weight	400000 g/mol	Margolies' equation
Average particle size, D50	20 µm	laser scattering

Rheological properties

Melt mass-flow rate	3.6 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	21.6 kg	
Viscosity number	400 cm ³ /g	ISO 307, 1157, 1628
Intrinsic viscosity	400	ISO 307, 1157, 1628

Typical mechanical properties

Tensile Modulus	1200 MPa	ISO 527-1/-2
Yield stress, 50mm/min	27 MPa	ISO 527-1/-2
Yield strain, 50mm/min	10 %	ISO 527-1/-2
Stress at 50% strain	18 MPa	ISO 527-1/-2
Stress at break, 50mm/min	34 MPa	ISO 527-1/-2
Nominal strain at break	770 %	ISO 527-1/-2
Elongational stress, 150/10	<0.05 MPa	ISO 21304-2
Charpy double notched impact strength, 23°C	30 kJ/m ²	ISO 21304-2

Tribological properties

Relative Wear (based on GUR 4120=100), sandslurry method	320	Internal
---	-----	----------

Other properties

Density	950 kg/m ³	ISO 1183
Bulk density	300 kg/m ³	ISO 60