



Electroplating ABS POLYLAC® PA-726M

Product Description: Electroplating

Properties	ISO Test Method	Test Condition	Unit	PA-726M
Melt Flow Index	1133	220°C×10KG	ml/10 min	23
Mass Density	1183	23 °C	g/cm ³	1.04
Tensile Strength	527	50 mm/min, yield	MPa	42
		50 mm/min, break	MPa	32
Tensile Elongation	527	50 mm/min	%	70
Flexural Strength	178	2 mm/min	MPa	63
Flexural Modulus		2 mm/min	GPa	2.1
Izod Impact Strength	180/1A	23°C, Notched	KJ/m ²	20
		-30°C, Notched	KJ/m ²	9
Charpy Impact Strength	179	23 °C Notched	KJ/m ²	22
		-30 °C Notched	KJ/m ²	10
Vicat Softening Temp.	306	1 Kg,50 °C/hr	°C	103
		5 Kg,50 °C/hr	°C	95
Heat Distortion Temp.	75/A	1.8 MPa Unannealed	°C	81
		1.8 MPa Annealed	°C	96
Coefficient of Linear Thermal Expansion	11359	-	-	8.7 x 10 ⁻⁵
Flammability	-	UL-94	-	1.5mm HB
Mold Shrinkage	294-4	-	%	0.4~0.7
Symbol	1043	-	-	>ABS<