

CHIMEI

a step up

General ABS POLYLAC® PA-757H

Product Description: Better balance in high flow and high impact, High gloss performance.

Properties	ISO Test Method	Test Condition	Unit	PA-757H
Melt Flow Index	1133	220°C×10KG	ml/10 min	30
Mass Density	1183	23 °C	g/cm ³	1.04
Tensile Strength	527	50 mm/min, yield	MPa	39
		50 mm/min, break	MPa	31
Tensile Elongation	527	50 mm/min	%	60
Flexural Strength	178	2 mm/min	MPa	61
Flexural Modulus		2 mm/min	GPa	2
Izod Impact Strength	180/1A	23°C, Notched	KJ/m ²	25
		-30°C, Notched	KJ/m ²	12
Charpy Impact Strength	179	23°C, Notched	KJ/m ²	26
		Charpy -30°C, Notched	KJ/m ²	13
Vicat Softening Temp.	306	50°C/hr;1KG	°C	105
		50°C/hr;5KG	°C	97
Heat Distortion Temp.	75/A	1.8MPa, unannealed	°C	83
		1.8MPa, annealed	°C	98
Coefficient of Linear Thermal Expansion	11359	-	-	8.6 x 10 ⁻⁵
Flammability	-	UL-94	-	1.5mm HB
Mold Shrinkage	294-4	-	%	0.4~0.7
Symbol	1043	-	-	>ABS<