

## Transparent MABS POLYLAC® PA-758R

Product Description: Transparent, Chemical resistant

Properties	ISO Test Method	Test Condition	Unit	PA-758R
Melt Flow Index	1133	200°C×5KG	ml/10 min	2.2
Mass Density	1183	23 °C	g/cm <sup>3</sup>	1.08
Tensile Strength	527	50 mm/min, yield	MPa	45
		50 mm/min, break	MPa	33
Tensile Elongation	527	50 mm/min	%	60
Flexural Strength	178	2 mm/min	MPa	62
Flexural Modulus		2 mm/min	GPa	2.1
Izod Impact Strength	180/1A	23 °C Notched	KJ/m <sup>2</sup>	15
		-30 °C Notched	KJ/m <sup>2</sup>	8
Charpy Impact Strength	179	23 °C Notched	KJ/m <sup>2</sup>	15
		-30 °C Notched	KJ/m <sup>2</sup>	8
Vicat Softening Temp.	306	1 Kg,50 °C/hr	°C	102
		5 Kg,50 °C/hr	°C	94
Heat Distortion Temp.	75/A	1.8 MPa Unannealed	°C	75
		1.8 MPa Annealed	°C	95
Coefficient of Linear Thermal Expansion	11359	-	-	8.7 x 10 <sup>-5</sup>
Flammability	-	UL-94	-	1.5mm HB
Mold Shrinkage	294-4	-	%	0.3 ~ 0.7
Symbol	1043	-	-	>MABS<