

CHIMEI

a step up

Flame Retardant ABS POLYLAC® PA-765A

Product Description: F.R. High flow

Properties	ISO Test Method	Test Condition	Unit	PA-765A
Melt Flow Index	1133	220°C×10KG	ml/10 min	48
Mass Density	1183	23 °C	g/cm ³	1.17
Tensile Strength	527	50 mm/min, yield	MPa	39
		50 mm/min, break	MPa	29
Tensile Elongation	527	50 mm/min	%	10
Flexural Strength	178	2 mm/min	MPa	56
Flexural Modulus		2 mm/min	GPa	1.8
Izod Impact Strength	180/1A	23°C, Notched	KJ/m ²	22
		-30°C, Notched	KJ/m ²	10
Charpy Impact Strength	179	23 °C Notched	KJ/m ²	23
		-30 °C Notched	KJ/m ²	10
Vicat Softening Temp.	306	1 Kg,50 °C/hr	°C	93
		5 Kg,50 °C/hr	°C	79
Heat Distortion Temp.	75/A	1.8 MPa Unannealed	°C	76
		1.8 MPa Annealed	°C	84
Coefficient of Linear Thermal Expansion	11359	-	-	8.48 x 10 ⁻⁵
Flammability	-	UL-94	-	1.5mm V-1 2.1mm V-0 2.1mm 5VB 2.5mm 5VA
Mold Shrinkage	294-4	-	%	0.3~0.6
Symbol	1043	-	-	>ABS-FR(17)<