

**CHIMEI**

a step up

**High Heat ABS POLYLAC® Characteristics PA-777B**

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	耐熱級 HIGH HEAT
				PA-777B
熔融指數 Melt Flow Index	D1238	200 °C, 5 Kg	g/10 min	-
		220 °C, 10 Kg		7.5
比重 Mass Density	D792	23 °C	-	1.03
硬度 Hardness	D785	-	R Scale	112
拉伸強度 (屈服) Tensile Strength (Yield)	D638	6 mm/min	Kg/cm <sup>2</sup>	440
			lb/in <sup>2</sup>	6240
延伸率 Tensile Elongation	D638	6 mm/min	%	15
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm <sup>2</sup>	650
			lb/in <sup>2</sup>	9200
彎曲彈性模數 Flexural Modulus	D790	2.8 mm/min	10 <sup>4</sup> Kg/cm <sup>2</sup>	2.2
			10 <sup>5</sup> lb/in <sup>2</sup>	3.1
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	6.4 mm, 23°C	Kg-cm/cm	20
			ft-lb/in	3.7
		3.2 mm, 23°C	Kg-cm/cm	23
			ft-lb/in	4.3
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	115
			°F	239
熱變形溫度 Heat Distortion Temp.	D648	1.8 MPa Annealed	°C	107
			°F	225
		1.8 MPa Unannealed	°C	97
			°F	207
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm HB