



Transparent MABS POLYLAC® PA-758

Product Description: Transparent

Properties	ISO Test Method	Test Condition	Unit	PA-758
Melt Flow Index	1133	200°C×5KG	ml/10 min	3.0
Mass Density	1183	23 °C	g/cm ³	1.08
Tensile Strength	527	50 mm/min, yield	MPa	42
		50 mm/min, break	MPa	33
Tensile Elongation	527	50 mm/min	%	40
Flexural Strength	178	2 mm/min	MPa	57
Flexural Modulus		2 mm/min	GPa	1.9
Izod Impact Strength	180/1A	23°C, Notched	KJ/m ²	14
		-30°C, Notched	KJ/m ²	7
Charpy Impact Strength	179	23 °C Notched	KJ/m ²	14
		-30 °C Notched	KJ/m ²	7
Vicat Softening Temp.	306	1 Kg,50 °C/hr	°C	104
		5 Kg,50 °C/hr	°C	96
Heat Distortion Temp.	75/A	1.8 MPa Unannealed	°C	77
		1.8 MPa Annealed	°C	97
Coefficient of Linear Thermal Expansion	11359	-	-	9.0 x 10 ⁻⁵
Flammability	-	UL-94	-	1.5mm HB
Mold Shrinkage	294-4	-	%	0.3 ~ 0.7
Symbol	1043	-	-	>MABS<