

High Heat PC/ABS WONDERLOY® Characteristics PC-540A

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	耐熱級 HIGH HEAT
				PC-540A
比重 Mass Density	D792	23 °C	-	1.18
硬度 Hardness	D785	-	M Scale	119
成型收縮率 Mould Shrinkage	D955		%	0.4~0.6
拉伸強度 (屈服) Tensile Strength (Yield)	D638	6 mm/min	Kg/cm ²	600
延伸率 Tensile Elongation	D638	6 mm/min	%	100
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm ²	900
彎曲彈性模數 Flexural Modulus	D790	2.8 mm/min	10 ⁴ Kg/cm ²	2.5
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	3.2 mm, 23°C	Kg-cm/cm	45
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	108
熱變形溫度 Heat Distortion Temp.	D648	Unannealed	°C	86
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm V-0 2.0 mm 5VB