

PMMA ACRYREX® CM-220HT

Product Description 產品敘述: High heat resistant

物性 Properties	ISO 測試方法 ISO Test Method	測試條件 Test Condition	單位 Unit	CM-220HT
熔融指數 Melt Flow Index	1133	230°C×3.8KG	ml/10 min	2.8
比重 Mass Density	1183	23 °C	g/cm ³	1.19
拉伸強度 Tensile Strength	527	5 mm/min, yield	MPa	70
		5 mm/min, break	MPa	70
延伸率 Tensile Elongation	527	5 mm/min	%	12
彎曲強度 Flexural Strength	178	2 mm/min	MPa	103
彎曲彈性模數 Flexural Modulus		2 mm/min	GPa	2.8
IZOD 衝擊強度 Izod Impact Strength	180/1A	23 °C Notched	KJ/m ²	2
		-30 °C Notched	KJ/m ²	-
Charpy 衝擊強度 Charpy Impact Strength	179	23 °C Notched	KJ/m ²	2
		-30 °C Notched	KJ/m ²	-
維氏軟化溫度 Vicat Softening Temp.	306	1 Kg,50 °C/hr	°C	121
		5 Kg,50 °C/hr	°C	113
熱變形溫度 Heat Distortion Temp.	75/A	1.8 MPa Unannealed	°C	99
		1.8 MPa Annealed	°C	108
線膨脹係數 Coefficient of Linear Thermal Expansion	11359	-	-	6 X 10 ⁻⁵
燃燒等級 Flammability	-	UL-94	-	1.5mm HB
成型收縮率 Mold Shrinkage	294-4	-	%	0.2~0.6
標記 Symbol	1043	-	-	>PMMA<