



# Bayblend® M303 FR

阻燃级别 / 非增强的

(PC+ABS)-Blend; Vicat/B 120 temperature = 115°C; suitable for use in electrical and electronic devices; Manufactured according to GMP; tested only according to ISO 10993-5 and ISO 10993-10 for contact with uncompromised skin only; for questions regarding biocompatibility we ask for an email inquiry under plastics@covestro.com

PC+ABS-FR(40)

性能	测试条件	单位	标准	数值
<b>流变性能</b>				
C 熔融指数 (体积)	260 ° C/ 5 kg	cm <sup>3</sup> /10 min	ISO 1133	11
C 熔体黏度	1000 s <sup>-1</sup> / 260 ° C	Pa·s	b. o. ISO 11443-A	410
C 成型收缩率, 流动方向/垂直流动方向	Value range based on general practical experience	%	b. o. ISO 2577	0.5 - 0.7
<b>机械性能</b>				
C 抗拉模量	1 mm/min	MPa	ISO 527-1,-2	2650
C 屈服应力	50 mm/min	MPa	ISO 527-1,-2	69
C 屈服应变	50 mm/min	%	ISO 527-1,-2	5
C 名义断裂拉伸应变	50 mm/min	%	ISO 527-1,-2	> 50
C 断裂应力	50 mm/min	MPa	ISO 527-1,-2	53
C Izod 冲击强度	23 ° C	kJ/m <sup>2</sup>	ISO 180/U	N
C Izod 缺口冲击强度	23 ° C	kJ/m <sup>2</sup>	ISO 180/A	40
C Izod 缺口冲击强度	-30 ° C	kJ/m <sup>2</sup>	ISO 180/A	10
<b>热性质</b>				
C 热变形温度	1.80 MPa	°C	ISO 75-1,-2	98
C 热变形温度	0.45 MPa	°C	ISO 75-1,-2	106
C 维卡软化温度	50 N; 50 ° C/h	°C	ISO 306	113
C 维卡软化温度	50 N; 120 ° C/h	°C	ISO 306	115
C 热膨胀系数, 流动方向	23 to 55 ° C	10 <sup>-4</sup> /K	ISO 11359-1,-2	0.68
C Coefficient of linear thermal expansion, normal	23 to 55 ° C	10 <sup>-4</sup> /K	ISO 11359-1,-2	0.72
C Burning behavior UL 94 (1.5 mm) [UL 认可]	1.5 mm	Class	UL 94	V-0
C 可燃性试验UL94 [UL 认可]	0.75 mm	Class	UL 94	V-2
<b>电性能 (23 ° C/50 % 相对湿度)</b>				
C 相对介电常数	100 Hz	-	IEC 60250	3.2
C 相对介电常数	1 MHz	-	IEC 60250	3.1
C 损耗因数	100 Hz	10 <sup>-4</sup>	IEC 60250	37
C 损耗因数	1 MHz	10 <sup>-4</sup>	IEC 60250	75
C 体积电阻率		Ohm·m	IEC 62631-3-1	1E15
C 表面电阻率		Ohm	IEC 62631-3-2	1E17
C Electrical strength	1 mm	kV/mm	IEC 60243-1	35
<b>其他性能 (23 ° C)</b>				
C 吸水性 (饱和值)	Water at 23 ° C	%	ISO 62	0.5
C 密度		kg/m <sup>3</sup>	ISO 1183-1	1190



# Bayblend® M303 FR

性能	测试条件	单位	标准	数值
----	------	----	----	----

建议成型工艺参数说明:

C 熔体温度		°C	-	240 - 270
C 标准熔体温度		°C	-	260
C 料管进料段温度		°C	-	220 - 230
C 料管中间段温度		°C	-	225 - 235
C 料管前段温度		°C	-	230 - 240
C 喷嘴温度		°C	-	255 - 265
C 模具温度		°C	-	60 - 90
C 保压压力 (%实际最大注射压力)		%	-	50 - 75
C 熔体背压		bar	-	50 - 150
C 螺杆转速		m/s	-	0.05 - 0.2
C 注射量		%	-	30 - 70
C 干空气下干燥温度		°C	-	80
C 干空气下干燥时间		h	-	4
C 最大含水量 (%)		%	-	<= 0.02
C 排气槽深度		mm	-	0.025 - 0.075

C 这些性能数据来源于 CAMPUS 塑料数据库并且依据 ISO 10350 标准的国际分类原则