



Panlite® B-8110R

TEIJIN LIMITED - Polycarbonate

General Information

Product Description

Carbon fiber reinforced grades-10% Carbon fiber

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Carbon Fiber, 10% Filler by Weight		
Features	• Creep Resistant	• High Rigidity	
Uses	• Camera Applications	• Industrial Applications	
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.40 to 0.60	%	
Flow : 4.00 mm	0.10 to 0.30	%	
Water Absorption (24 hr, 23°C)	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7700	MPa	ISO 527-2/1
Tensile Stress (Break)	110	MPa	ISO 527-2/5
Tensile Strain (Break)	2.5	%	ISO 527-2/5
Flexural Modulus ²	7400	MPa	ISO 178
Flexural Stress ²	165	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	8.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	35	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	149	°C	ISO 75-2/B
Heat Deflection Temperature (1.8 MPa, Unannealed)	146	°C	ISO 75-2/A
Vicat Softening Temperature	152	°C	ISO 306/B50
CLTE - Flow	3.0E-5	cm/cm/°C	ISO 11359-2
CLTE - Transverse	6.0E-5	cm/cm/°C	ISO 11359-2
RTI Elec (1.5 mm)	80.0	°C	UL 746
RTI Imp (1.5 mm)	80.0	°C	UL 746
RTI Str (1.5 mm)	80.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0 to 1.0E+3	ohms	IEC 60093
Volume Resistivity	1.0E+2 to 1.0E+4	ohms-cm	IEC 60093

Panlite® B-8110R
TEIJIN LIMITED - Polycarbonate

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.75 mm		V-2	
3.0 mm		V-1	

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 mm/min