

Chemlon® 66CF4

Teknor Apex 公司 - 聚酰胺 66

注射	干燥 单位制
Back Pressure	Low
Screw Speed	Moderate

注射说明

No drying is necessary unless the material has been exposed to air for longer than three hours. The appearance of splash marks on the surface of mouldings indicates excessive moisture is present.