

# UMG ABS, Ltd.

TECHNOLOGY DEPARTMENT

## 物 性 表

商 标 (TRADEMARK) : UMG ALLOY®

品 级 (GRADE) : TC-6F

性能项目 Property	测试方法 TestMethod	测试条件 Condition	单位 Unit	TC-6F
冲击强度 CharpyImpactStrength	ISO 179	23 deg. C	kJ/m <sup>2</sup>	50
		-30 deg. C		-
拉伸强度 TensileStrength	ISO 527	23 deg. C	MPa	48
拉伸模量 TensileModulus		23 deg. C	MPa	2000
弯曲强度 FlexuralStrength	ISO 178	23 deg. C 2mm/min	MPa	80
弯曲模量 FlexuralModulus			MPa	2200
硬度 RockwellHardness	ISO 2039	23 deg. C	R-scale	110
热变形温度 T. D. U. L.	ISO 75	1.80MPa Flatwise	deg. C	99
密度 Density	ISO 1183	23 deg. C	g/cm <sup>3</sup>	1.11
熔融指数 M. V. R.	ISO 1133	220 °C	cm <sup>3</sup> /10min	8.5
模具收缩率 MoldShrinkage	ISO 294-4	23 deg. C	%	0.5-0.7
线性膨胀系数 C. L. T. E.	ISO 11359-2	-	cm/cm/deg. C(x10 <sup>-5</sup> )	8.5
阻燃性 ULFileNo. E47016	UL 94	-	mm	1.5 HB
		-	mm	-
		-	mm	-