

Titan A400CF

樹脂 RESIN : ACRYLONITRILE BUTADIENE STYRENE RESIN

產品說明 PRODUCT DESCRIPTION : ADD 20%CF 填充。

項目 Properties	單位 Unit	測試方法 method	數值 Value
顏色 Color	-	-	Black
比重 specific gravity	g/cm ³	ISO 1183	1.13
拉伸強度 Tensile strength 拉伸率 Tensile Elongation	MPa	ISO 527-1,2	105 >1
彎曲強度 Flexural strength 彎曲模數 Flexural modulus	MPa	ISO 178	152 11000
衝擊強度(有缺口) Charpy impact strength(notched)	kJ/m ²	ISO 179/1eA	7
熱變形溫度(1.8MPa) Heat Deflection Temperature(1.8MPa)	°C	ISO 75-1,2	98
體積阻抗 Volume resistivity 表面阻抗 Surface resistivity	Ω•cm Ω	IEC 60093	1×10 ^{3~5} 1×10 ^{3~5}
耐燃性 Flammability		UL 94	HB
模收縮 Mold shrinkage	%	50x70x3 mm	0.1~0.3
成型條件 MOLDING CONDITION	°C	乾燥條件 Drying	80~100x 4Hrs
		料管溫度 Melt Temp.	200~240
		模具溫度 Mold Temp.	60~100
	%	射出壓力 Inject. Press.	30~70
射出速度 Inject. Velocity		20~50	

*以上數值為材料的代表性測試值、並非該規格材料的最低值。

*All property values shown in this data sheet are the representative values and not minimum value of this material.