

Titalon 2200ST

樹酯RESIN：POLYAMIDE66 RESIN

產品說明PRODUCT DESCRIPTION：低溫耐衝擊

項目 Properties	單位 Unit	測試方法 method	數值 Value
顏色 Color	-	-	Natural
比重 specific gravity	g/cm ³	ISO 1183	1.10
拉伸強度 Tensile strength 拉伸率 Tensile Elongation	MPa	ISO 527-1,2	51 >50
彎曲強度 Flexural strength 彎曲模數 Flexural modulus	MPa	ISO 178	52 1850
衝擊強度(有缺口) Charpy impact strength(notched)	kJ/m ²	ISO 179/1eA	50
熱變形溫度(1.8MPa) Heat Deflection Temperature(1.8MPa)	°C	ISO 75-1,2	60
體積阻抗 Volume resistivity 表面阻抗 Surface resistivity	Ω•cm Ω	IEC 60093	1×10 ¹⁵ 1×10 ¹⁴
耐燃性 Flammability		UL 94	HB
模收縮 Mold shrinkage	%	50x70x3 mmt	1.2~1.8
成型條件 MOLDING CONDITION	°C	乾燥條件 Drying	80~100x 4Hrs
		料管溫度 Melt Temp.	260~290
		模具溫度 Mold Temp.	60~100
	%	射出壓力 Inject. Press.	30~70
射出速度 Inject. Velocity		30~60	

*以上數值為材料的代表性測試值、並非該規格材料的最低值。

*All property values shown in this data sheet are the representative values and not minimum value of this material.