

## ASA Resin ASA 树脂 TOYOLAC™ TA42C X01

**FEATURE 特点**

High Heat

高耐热

**APPLICATION 用途**

Building Materials, Automotive Parts

建筑材料, 汽车配件, 一般应用

**TECHNICAL DATA SHEET 技术数据表**

PROPERTY 性能	TEST METHOD 测试方法	TEST CONDITION 测试条件	UNITS 单位	TOYOLAC™ TA42C X01
<b>Physical Properties 物理性能</b>				
Density 密度	ISO 1183	23 °C	kg/m <sup>3</sup>	1060
Melt Flow Rate 流动系数	ISO 1133	220 °C / 10 kg	g/10 min	20
Mold Shrinkage 成型收缩率	-	-	-	-
Glass Content 玻纤含量	-	-	-	-
<b>Mechanical Properties 机械性能</b>				
Charpy Impact Strength, Notched Charpy 耐冲击强度, 缺口	ISO 179/1eA	23 °C / 50% RH	kJ/m <sup>2</sup>	10
Tensile Strength 拉伸强度-降伏点	ISO 527	50 mm / min	MPa	45
Tensile Elongation at Break 拉伸伸长率-断裂点	ISO 527	50 mm / min	%	5
Tensile Modulus 拉伸模数	ISO 527	1 mm / min	MPa	2200
Flexural Strength 弯曲强度	ISO 178	2 mm / min	MPa	70
Flexural Modulus 弯曲模数	ISO 178	2 mm / min	MPa	2180
<b>Thermal Properties 热性能</b>				
Deflection Temperature Under Load 热变形温度	ISO 75	1.8 MPa / 120 °C/hr	°C	85
<b>Appearance 表面</b>				
Glossiness 光泽度	-	-	-	-
Light Transmittance 光线透光率	-	-	-	-
Haze 模糊系数	-	-	-	-
<b>Flammability 燃烧性</b>				
Flammability 燃烧性	-	-	-	-

TORAY PLASTICS (MALAYSIA) SDN BERHAD 东丽塑料大马有限公司