



SBS -3201 Polymer Data

- Polymerization System -- Solution Polymerization, styrene-butadiene block copolymer
- Stabilizer -- Non-staining
- Characteristics -- Medium molecular weight
- High strength
- Easy processing
- Good solubility in common adhesive solvent
- Application -- Mainly for plastic modification, adhesives(HMA), asphalt modification, elastic compounds, shoe soles.

Specification Range

<u>Polymer Properties</u>		<u>Specification Range</u>		<u>Test Method</u>
		<u>min</u>	<u>max</u>	
Bound Styrene	(%)	28.5	31.5	K62-TPPC-09
Volatile matter	(%)	—	0.5	K62-TPFP-01
Yellow Index		—	4.0	K62-TPFP-04
Ash	(%)	—	0.2	ASTM D-5667
Specific gravity		0.95 Typical		ASTM D-792
Gel	(%)	—	0.1	K62-TPFP-16
Toluene Sol. Vis. 25°C	(5%,cps)	7.5	11.5	ASTM D-3616
Hardness	(Type A)	80 Typical		ASTM D-2240