

**超塑烯® UE3330****EVATHENE® UE3330****乙烯醋酸乙烯酯共聚合樹脂****ETHYLENE-VINYL ACETATE COPOLYMER RESINS**

<b>概述</b>	<b>Description</b>
超塑烯® UE3330 是一種乙烯醋酸乙烯酯共聚合樹脂，可應用在高彈性、低硬度的鞋材發泡。	EVATHENE® UE3330 is an ethylene-vinyl acetate copolymer resin (EVA) for use in shoe sole foaming with high rebound property.
<b>特性</b>	<b>Characteristics</b>
<ul style="list-style-type: none"> <li>◇ 優異的加工性</li> <li>◇ 良好的光學性質</li> <li>◇ 卓越的電氣性能</li> <li>◇ 彈性</li> <li>◇ 低溫柔軟性很好</li> <li>◇ 黏著力優異</li> </ul>	<ul style="list-style-type: none"> <li>◇ Outstanding processability</li> <li>◇ Good optical properties</li> <li>◇ Excellent electrical properties</li> <li>◇ Elasticity</li> <li>◇ Low temperature flexibility</li> <li>◇ Excellent adhesion</li> </ul>
<b>應用</b>	<b>Applications</b>
<ol style="list-style-type: none"> <li>1. 發泡鞋材</li> <li>2. 一般摻合應用</li> </ol>	<ol style="list-style-type: none"> <li>1. Shoe sole foaming</li> <li>2. General compounding</li> </ol>

**物理性質 Physical Properties**

<b>項目</b> Properties	<b>試驗方法</b> Test Method	<b>數 值</b> Typical Value
VA 含量 VA Content (wt%)	USI	33
熔融指數 Melt Index (g/10min)	ASTM D1238	30
密度 Density (g/cm <sup>3</sup> )	ASTM D792	0.956
斷裂點抗張強度(模片) Tensile Strength(Molded) (Break) (kg/ cm <sup>2</sup> )	ASTM D638	70
斷裂點伸長率 (模片) Ultimate Elongation(Molded) (%)	ASTM D638	900
環球軟化溫度 Ring and Ball Softening Point (°C)	ASTM E28	113
熔點 Melt Point (°C)	ASTM D3418	64
硬度(蕭氏 A) Hardness (Shore A)	ASTM D2240	63